



Material data sheet PA 66 black

Chemical Designation: Polyamide 66
 DIN-abbreviation: PA 66
 Colour / Fillers: black opaque / molybdenum disulfide
 Density: 1,15 g/cm³

Data generated directly after machining
(standard climate Germany).

Main features

- high toughness
- good wear properties
- high strength
- high stiffness
- resistant to many oils, greases and fuels
- good slide and wear properties
- good weldable and bondable

Target Industries

- mechanical engineering
- automotive industry
- aircraft an aerospace technology
- electronics

Characteristics

mechanical properties	parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)	1 mm / min	3200	MPa	DIN EN ISO 527-2 1)	1) For tensile test: specimen type 1b 2) For flexural test: support span 64 mm, norm specimen. 3) Specimen 10 x 10 x 10 mm 4) Specimen 10 x 10 x 50 mm, modulus range between 0,5 and 1% compression. 5) For Charpy test: support span 64 mm, norm specimen. n. b. = not broken
Tensile strength	50 mm / min	84	MPa	DIN EN ISO 527-2	
Tensile strength at yield	50 mm / min	83	MPa	DIN EN ISO 527-2	
Elongation at yield (tensile test)	50 mm / min	10	%	DIN EN ISO 527-2	
Elongation at break (tensile test)	50 mm / min	25	%	DIN EN ISO 527-2	
Flexural strength	2 mm / min, 10 N	114	MPa	DIN EN ISO 178 2)	
Modulus of elasticity (flexural test)	2 mm / min, 10 N	3100	MPa	DIN EN ISO 178	
Compression strength	1% / 2% / 5% 5 mm / min, 10 N	20/38/86	MPa	EN ISO 604 3)	
Compression modulus	5 mm / min, 10 N	2700	MPa	EN ISO 604 4)	
Impact strength (Charpy)	max. 7,5 J	n. b.	kJ/m ²	DIN EN ISO 179-1eU 5)	
Notched impact strength (Charpy)	max. 7,5 J	5	kJ/m ²	DIN EN ISO 179-1eA	
Shore hardness	D	81		DIN EN ISO 868	





Material data sheet PA 66 black

thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		52	°C	DIN EN ISO 11357 1)	1) Found in public sources. 2) Found in public sources. Individual testing regarding application conditions is mandatory.
Melting temperature		253	°C	DIN EN ISO 11357	
Service temperature	short term	170	°C		
Service temperature	long term	100	°C		
Thermal expansion (CLTE)	23-60 °C, long	10	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100 °C, long	10	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Specific heat		1.5	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.36	W/(K*m)	ISO 22007-4:2008	

electrical properties	parameter	value	unit	norm	comment
surface resistivity	Silver electrode, 23 °C, 12% r.h.	10 ¹⁴	Ω	DIN IEC 60093 1)	1) Specimen in 20 mm thickness 2) Due to the black colourant and moisture uptake of the material the electrical insulation properties cannot be 100% guaranteed, despite single measurements suggesting otherwise 3) Specimen in 1 mm thickness
volume resistivity	Silver electrode, 23 °C, 12% r.h.	10 ¹⁴	Ω*cm	DIN IEC 60093 2)	
Dielectric strength	23 °C, 50% r.h.	35	kV/mm	ISO 60243-1 3)	
Resistance to tracking (CTI)	Platin electrode, 23 °C, 50% r.h., solvent A	600	V	DIN EN 60112	

other properties	parameter	value	unit	norm	comment
Water absorption	24 h / 96 h (23 °C)	0.2 / 0.4	%	DIN EN ISO 62 1)	1) Ø ca. 50 mm, h = 13 mm 2) (+) limited resistance 3) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Resistance to hot water/bases		(+)		- 2)	
Resistance to weathering		(+)			
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10 3)	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Technical changes reserved.

Date: 2024/07/15

